



GlueDots[®]
Adhesive Products

REACH Compliance

Glue Dots[®] Brand Adhesive Products are produced using a variety of synthetic, rubber-based adhesives. Based upon information provided by our suppliers and to the best of our knowledge, Glue Dots' adhesives and liners do not contain any of the Substances of Very High Concern (SVHC) in accordance to REACH-SVHC EC 1907/2006, effective June 18, 2012:

2,4-Dinitrotoluene	2-Ethoxyethanol
2-Methoxyethanol	
4,4'-Diaminodiphenylmethane (MDA)	Acrylamide
5-tert-butyl-2,4,6-trinitro-m-xylene (musk xylene)	Aluminosilicate Refractory Ceramic Fibres
Alkanes, C10-13, chloro	Anthracene
Ammonium dichromate	Anthracene paste
Anthracene oil	Anthracene fraction
Anthracene paste, distn. lights	Benzyl butyl phthalate (BBP)
Anthracene-low	Bis (tributyltin) oxide (TBTO)
Bis (2-ethyl(hexyl)phthalate) (DEHP)	Chromic acid
Boric acid	Chromium trioxide
Dichromic acid	Colbalt(II) carbonate
Colbalt dichloride	Colbalt(II) dinitrate
Colbalt(II) diacetate	Diarsenic pentaoxide
Colbalt(II) sulphate	Dibutyl phthalate (DBP)
Diarsenic trioxide	
Diisobutyl phthalate	
Disodium tetraborate, anhydrous	Alpha-hexabromocyclododecane
Hexabromocyclododecane (HBCDD)	
Beta-hexabromocyclododecane	
Gamma-hexabromocyclododecane	Lead chromate
Lead chromate molybdate sulphate red	Lead hydrogen arsenate
Lead sulfochromate yellow	Pitch, coal tar, high temp
Potassium chromate	Potassium dichromate
Sodium chromate	Sodium dichromate, dihydrate
Tetraboron disodium heptaoxide, hydrate	Trichloroethylene
Triethyl arsenate	Tris (2-chloroethyl) phosphate
Zirconia Aluminosilicate Refractory Ceramic Fibres	2-Ethoxyethyl acetate
Strontium chromate	Hydrazine
1-Methyl-2-pyrrolidone	1,2,3-Trichloropropane
1,2-Benzenedicarboxylic acid, di-C7-11 branched and linear alkyl esters	
1,2-Benzenedicarboxylic acid, di-C6-8 branched alkyl esters, C7-rich	



Lead styphnate	Lead diazide, Lead azide
Lead dipicrate	Phenolphthalein
2,2'-Dichloro-4,4'-methylenedianiline	N,N-dimethylacetamide
Trilead diarsenate	Calcium arsenate
Arsenic acid	Bis(2-methoxyethyl) ether
1,2-Dichloroethane	
4-(1,1,3,3-Tetramethylbutyl)phenol; 4-tert-octyl phenol	
2-Methoxyaniline; o-Anisidine	Bis(2-methoxyethyl) phthalate
Bis(2-methoxyethyl) ether	
Formaldehyde, oligomeric reaction products with aniline (technical MDA)	
Pentazinc chromate octahydroxide	Dichromium tris(chromate)
Potassium hydroxyoctaoxodizincatedichromate	

Zirconia Aluminosilicate and Aluminosilicate Refractory Ceramic Fibres covered by index # 650-017-00-8 in Annex VI, part 3, table 3.1 of Regulation (EC) No 1272/2008 of the European Parliament and of the Council of 16 December 2008 on classification, labeling and packaging of substances and mixtures, and fulfill the three following conditions:

- oxides of aluminum, silicon and zirconium or oxides of aluminum and silicon are the main components present (in the fibres) within variable concentration ranges.
- fibres has a length weighted geometric mean diameter less two standard geometric errors of 6 or less micrometres.
- alkaline oxide and alkali earth oxide ($\text{Na}_2\text{O} + \text{K}_2\text{O} + \text{CaO} + \text{MgO} + \text{BaO}$) content less or equal to 18% by weight.

1,2-bis(2-methoxyethoxy)ethane (TEGDME; triglyme)
1,2-dimethoxyethane; ethylene glycol dimethyl ether (EGDME)
Formamide
Lead(II) bis(methanesulfonate)
1,3,5-Tris(oxiran-2-ylmethyl)-1,3,5-triazinane-2,4,6-trione (TGIC)
1,3,5-tris[(2S and 2R)-2,3-epoxypropyl]-1,3,5-triazine-2,4,6-(1H, 3H, 5H)-trione(-TGIC)
4-4'-bis(dimethylamino)benzophenone (Michler's ketone)
N,N,N',N'-tetramethyl-4,4'-methylenedianiline (Michler's base)
Diboron trioxide

[4-[[4-anilino-1-naphthyl][4-(dimethylamino)phenyl]methylene]-cyclohexa-2,5-dien-1-ylidene] dimethylammonium chloride (C.I. Basic Blue 26)*

[4-[4,4'-bis(dimethylamino)benzhydrylidene] cyclohexa-2,5-dien-1-ylidene]dimethylammonium chloride (C.I. Basic Violet 3)*

4-4'-bis(dimethylamino)-4''-(methylamino)trityl alcohol*

Bis[4-(dimethylamino)phenyl]-4(phenylamino) naphthalene-1-methanol (C.I. Solvent Blue 4)*

* with $\geq 0.1\%$ of Michler's ketone (EC No. 202-027-5) or Michler's base (EC No. 202-959-2)]